

## DEVELOPMENT AND CHARACTERIZATION OF BIODEGRADABLE FOOD PACKAGING FILMS FROM FOOD INDUSTRIAL WASTES

Muhammad Adnan Hafeez<sup>1,\*</sup>, Abid Aslam Maan<sup>1</sup>, Masood Sadiq Butt<sup>1</sup> and Muhammad Anjum Zia<sup>2</sup>

<sup>1</sup>National Institute of Food Science and Technology, Faculty of Food, Nutrition and Home Sciences, University of Agriculture, Faisalabad, Pakistan

<sup>2</sup>Department of Biochemistry, Faculty of Sciences, University of Agriculture, Faisalabad, Pakistan

\*Corresponding author's e-mail: Hafeez\_ma@outlook.com

The demand of food packaging has increased along with the food consumption. Among all types of packaging materials plastics are most commonly used owing to their good mechanical, barrier and permeability characteristics. However, plastics are totally non-biodegradable and their raw materials come from non-renewable resources. This has urged the researchers to explore biodegradable food packaging films from renewable resources. Natural polymers such as carbohydrate, starch, cellulose, hemicellulose or pectin can be effectively used for the synthesis of biodegradable food packaging films. Fruits and vegetables processing industries are producing huge amount of waste in the form of peels, seeds and pomace. Being rich source of biopolymers, these wastes can serve as a good source of raw material for synthesis of biodegradable packaging films. In the present research, three types of food industrial wastes (potato, citrus and apple residues) were used with varying glycerol concentrations to develop biodegradable food packaging films. The prepared films were analyzed on the basis of their thickness, water vapor permeability (WVP), opacity, mechanical properties and photo oxidation. Results showed that potato residue film was thicker (0.17 mm) and more opaque (97.45 AU nm) in comparison with citrus and apple residue films. Results for mechanical properties showed that potato residue film possessed greater tensile (8.99 MPa) and puncture strength (13.78 N). However, it exhibited lower elongation at break (9.54 %) compared to citrus and apple residue films. While citrus residue film showed higher elastic modulus compared to potato and apple residue films. Water vapor permeability of all the prepared films was comparable. Increased glycerol concentration in film forming solutions resulted in the increase in thickness, opacity, water vapor permeability and elongation at break of all the films. However, increased glycerol concentration caused a decrease in tensile strength, elastic modulus and puncture strength of all the films. The structure of organic compounds present in prepared biodegradable films was evaluated using Fourier Transform Infrared Spectroscopy (FTIR) technique.

**Keywords:** Food packaging, plastic packaging, biodegradable films, food industrial wastes.

### INTRODUCTION

The global packaging industry was reported to be of worth \$931.1 billion in 2018 and is expected to reach \$1177.7 billion in 2025 (Expresswire, 2019). The food packaging comprises the largest portion of this packaging cost amounting \$293 billion in 2018 and expected to reach \$423.27 billion in 2025 (Shahbandeh, 2019). Currently, petrochemical-based (polythelene, polyvenyl chloride, and polypropylene etc.) plastic films are used abundantly as packaging materials owing to their large availability and good mechanical strength (tensile properties), permeability to water vapors, carbon dioxide, oxygen, aroma compounds etc. and heat seal ability (Sorrentino *et al.*, 2007). These plastics originate from non-renewable resources and are totally non-biodegradable leading to serious disposal problems. The manufacturing process of plastic packaging also involves higher energy cost (Ferreira *et al.*, 2016). Toxic chemical ingredients present in the packaging material often

contaminate the food stuff. Keeping in view the issues related to plastic packaging materials, development of biodegradable packaging is not only a useful necessity but also an important environmental requirement (Siracusa *et al.*, 2008).

Biodegradable packaging materials are based on renewable resources, cost effective and are environment friendly (Shen *et al.*, 2015). Researchers are continuously exploring the biological sources suitable for the preparation of biodegradable films and coatings. Biodegradable films are prepared using natural biopolymers and biological materials such as polysaccharides, proteins, lipids, polyesters and derivatives (Franco *et al.*, 2017). Use of these natural biopolymers in food packaging films is highly safe because of the absence of toxins or harmful chemicals. These biopolymers break down into harmless products and get absorbed into the soil after being used (Khalil *et al.*, 2018). Biodegradable films and coatings possess ability to lower the metabolic rate of fruits and vegetables (Cardoso *et al.*, 2017). Properly formulated biodegradable films have been reported

to maintain the quality characteristics of a variety of fresh fruits and vegetables including strawberries (Mali and Grossmann, 2003; Gol *et al.*, 2013; Wang and Gao, 2013; Franco *et al.*, 2017), blueberries (Almenar *et al.*, 2010), carambola (Gol *et al.*, 2015), avocado (Aguilar-Mendez *et al.*, 2008), carrots (Mensitieri *et al.*, 2011) fresh cut carrots (Fai *et al.*, 2016), carrot slices (Moreira *et al.*, 2011) baby corn and Chinese cabbage (Pitak and Rakshit, 2011), minimally processed lettuce (Del Nobile *et al.*, 2008) fresh cut apples (McHugh and Senesi, 2000; Sangsuwan *et al.*, 2008; Chiumarelli and Hubinger, 2012), fresh cut papaya (Tapia *et al.*, 2008), acerolas (Ferreira *et al.*, 2016), tomatoes (Athmaselvi *et al.*, 2013), mango (Chonhenchob *et al.*, 2007), mango puree (Azeredo *et al.*, 2009), Hayward kiwifruit (Benítez *et al.*, 2013), grapes (Chauhan *et al.*, 2014), Red Crimson grapes (Fakhouri *et al.*, 2015), pineapple (Chonhenchob *et al.*, 2007) etc. by reducing respiration, gaseous exchange, moisture and solute migration and oxidative reaction rates (Cortez-Vega *et al.*, 2014). Fruits and vegetables have been used as an alternative to the direct use of biopolymers for the preparation of biodegradable films (McHugh and Olsen, 2004; Sothornvit and Pitak, 2007; Azeredo *et al.*, 2009; Du *et al.*, 2011; Azeredo *et al.*, 2012; Martelli *et al.*, 2013). The first scientific research on the potential of fruits and vegetables for development of biodegradable packaging materials was reported in 1990s. This paved the way for fruits and vegetables purees, extracts and pulp to be used in biodegradable packaging (Du *et al.*, 2008; Cerqueira *et al.*, 2011; Ravishankar *et al.*, 2012; Lorevice *et al.*, 2012; Martelli *et al.*, 2013; Torres *et al.*, 2015; Orsuwan *et al.*, 2016; Kadzińska *et al.*, 2019). However, fruits and vegetables are the essential components of a healthy diet and their direct consumption in biodegradable films can lead to the issues of food security forever growing populations. Industrial processing of fruits and vegetables produces an enormous amount of wastes in the form of peels, pulp and seeds etc. (Campos *et al.*, 2014; Ferreira *et al.*, 2015). These waste materials are a rich source of biopolymers (polysaccharides and dietary fibers) and bioactive compounds (Babbar *et al.*, 2011; Ajila and Rao, 2013). Owing to their low market value, most of these wastes are underutilized and are used as fertilizer and animal feed or rather discarded into soil representing not only an environmental issue but also wastage of potential nutrients and biopolymers (Park and Zhao, 2006). Proper handling and utilization of these materials in biodegradable film formation can provide new market for value added by products (Saravacos *et al.*, 2011). Potato is the major vegetable crop of Pakistan and is cultivated over an area of 177297 hectares with total annual production of 3974 thousand tons (Ahmed *et al.*, 2017). It is processed into a variety of products including potato chips, French fries, potato protein, potato powder etc. About half of the potato solids are wasted during its industrial processing. Potato peel accounts for 15 to 40% of this potato waste. (Ali

*et al.*, 2015). Citrus (orange) is the major fruit produced in Pakistan and is cultivated on 192230 hectares with an annual production of 2344 thousand tones (Ahmed *et al.*, 2017). Processing of citrus (into juices, essential oils and other products) produces massive amount of wastes in the form of pulp, peels and seeds. The resulting waste accounts for about 50% of the fresh fruit, comprising of approximately 10% seeds, 30-35% internal tissues and 60-65% peels. The waste is rich in pectin, cellulose and hemicellulose (Mannepula *et al.*, 2015). Apple is the fourth major fruit of Pakistan regarding production and is cultivated on 96928 hectares. Its annual production is reported to be 620 thousand tons (Ahmed *et al.*, 2017). Processing of apples generates peels, stems, seeds and soft tissues as by product which represents about 30% of the total input. This waste is rich in pectin and cellulose (Sablani *et al.*, 2009). The present study was planned to explore the potential of locally generated fruit and vegetable wastes for development and characterization of biodegradable food packaging films.

## MATERIALS AND METHODS

**Procurement and preparation of raw materials:** Fresh potatoes, citrus (orange) and apples were procured from fruits and vegetables market of Faisalabad. These fruits and vegetable were hand washed to remove the dust and other foreign matters. After washing, all the three commodities were manually peeled and subjected to juice extraction (apple and citrus only). The obtained peels and pomace were dried at 60°C for 6 to 8 hours in hot air oven. The dried residues (peels and pomace) were subjected to size reduction through grinding to get fine powder. This fine powder (residue flour) was then subjected to sieving through 40 (420 µm) mesh sieve to get residue flour of the uniform average particle sizes. Analytical grade glycerol, digestion tablets, sulfuric acid, sodium hydroxide, boric acid, petroleum ether, sodium azide,  $\alpha$  and  $\beta$  amylase, pectinase, cellulase, methyl red and ethylene blue indicators were obtained from Sigma-Aldrich (Steinheim, Germany).

**Proximate composition of residue flours:** Proximate composition of residue flours was analyzed according to the method described in AACC (2000). The moisture content was measured by hot air oven at 105±5°C. Ash content was estimated by charring and complete burning in muffle furnace at 550 °C for 5-6 hours till greyish end point. Crude protein was determined by kjeldhal method in three stages consisting of digestion with acid, distillation with base and boric acid and titration with acid neutralization. Crude fat was determined by extraction with n-Hexane in Soxhlet apparatus. Crude fiber was measured by igniting the sample at 550-650 °C for 3-5 hours in the muffle furnace after digesting it with acid and base. Following equation was used to determine the nitrogen free extracts (NFE) of the residue flours.

**Film preparation:** Three g of each residue flour was dissolved in 97ml distilled water to prepare three different film forming solutions. The solutions were pre-homogenized by Ultra-Turrax homogenizer (T18 D, IKA-Germany) at 20,000rpm for 5 minutes (Sablani *et al.*, 2009). The film forming solutions were subjected to stirring through magnetic stirrer for 1 hour to get the uniform mixture. Film forming mixtures were then subjected to sonication (400W) to disrupt the biopolymers in the solution. The said solutions were subjected to heating at 90°C for 30 minutes in water bath and cooled to 5°C (apple residue solution) or 20°C (potato and citrus residue solutions) in an ice box. A final homogenization of the film forming solutions was carried out at 20,000 rpm for 5 minutes after glycerol addition. Glycerol concentration was varied from 25% to 35% in all films. Finally, these solutions were subjected to degassing for the removal of air bubbles. The film forming solutions were cast on Teflon plates having 15.5 cm internal diameter. Approximately, 68 g of each solution was poured in the Teflon plates separately. After drying at  $23 \pm 2^\circ\text{C}$  and  $35 \pm 5\%$  relative humidity for 48 to 72 hours, the dried films were detached from the Teflon plates for further analyses (Kang and Min, 2010).

#### Film characterization

**Film thickness:** Each film sample was analyzed for its thickness at five different positions using digital micro-meter and average of these measurements were used for further analyses according the method described by Kang and Min (2010).

**Water vapor permeability:** The prepared films were sealed separately on permeation cells containing distilled water and were kept in the desiccator to measure the water vapor permeability. These permeation cells were weighed at regular intervals for 2-3 days to check the water vapor flux (Alves *et al.*, 2010).

**Opacity:** Prepared film samples were cut into  $1\text{cm} \times 3\text{cm}$  size and absorbance spectrum between 400-800 nm were measured after placing these samples on the inner side of the spectrophotometer (Model: U2020, Serial- 20A Irmeco, Germany) cell. Area under curve was considered as the opacity of the films and expressed as the absorbance units  $\times$  nano-meters (Mali *et al.*, 2004).

**Mechanical properties:** Films were cut into  $8\text{cm} \times 0.5\text{cm}$  size and held between the grips of tensile tester (TST-01, Cell Instruments, China). Tensile strength, elastic modulus and elongation at break of the film samples were recorded by using 5mm/minute crosshead speed (Almasi *et al.*, 2010). Moreover, film samples were cut into 40mm diameter and fixed on plate of tensile tester via adhesive tape to measure the puncture strength of the films. A cylindrical probe was moved perpendicularly at a constant speed of 1mm/s until the probe passed through the film. At rupture point, force-deformation curves were recorded (Mali *et al.*, 2004).

**Photo oxidation:** The prepared film samples of specific dimensions were analyzed through Fourier Transform

Infrared Spectroscopy (FTIR) to get the absorption spectra of the films. The interference of water vapors was reduced by equipping the instrument with dehumidifier (silica gel). An average of 20 scans were taken as spectra at a resolution of  $4\text{cm}^{-1}$  in the range of  $400\text{-}4,000\text{ cm}^{-1}$  through FTIR (Bruker Tensor 27) (Banisadr and Asempour, 2012).

## RESULTS AND DISCUSSIONS

**Proximate composition of residue flour:** Proximate analysis of residue flours of potato, citrus and apple is summarized in Table 1. The highest moisture content was observed for the potato residue flour ( $13.33 \pm 0.66\%$ ) followed by residue flours of citrus ( $10.0 \pm 0.50\%$ ) and apple ( $3.3 \pm 0.16\%$ ). Similarly, the highest protein contents were also recorded for the potato residue flour ( $15.31 \pm 0.76\%$ ) and lower protein content was found in residue flour of citrus ( $4.37 \pm 0.21\%$ ) and apple ( $8.33 \pm 0.41\%$ ). Residue flours of citrus and apple were found to have  $2 \pm 0.1\%$  fiber while potato residue flour exhibited  $1.4 \pm 0.07\%$  fiber. In terms of the fat content in the residue flour of apple had the higher content ( $4.59 \pm 0.22\%$ ) followed by citrus ( $4.46 \pm 0.22\%$ ) and potato ( $1.4 \pm 0.07\%$ ) residue flour. Ash content represents the mineral content of the sample. Highest ash contents were observed in potato residue flour ( $9.38 \pm 0.46\%$ ) followed by residue flours of citrus ( $4.89 \pm 0.24\%$ ) and apple ( $2.39 \pm 0.11\%$ ). The protein contents of apple residue flour were greater than the value of 6.7% reported by Akpabio *et al.* (2012). Fat content of potato residue flour was comparable with findings of Bretón-Toral *et al.* (2016) who stated it to be 2.1%. Romelle *et al.* (2016) reported fat content of citrus and apple peel powders to be  $8.70 \pm 0.65\%$  and  $9.96 \pm 1.52\%$ , respectively. Nitrogen free extract (NFE) represents the carbohydrate content and was calculated from the aforementioned proximate composition on difference basis. According to Table 1, the highest NFE was found in residual flour of apple ( $79.39 \pm 3.96\%$ ), which are similar with the outcomes of Akpabio *et al.* (2012). Lower NFE contents were observed in potato residue flour ( $57.97 \pm 2.89\%$ ) followed by residue flour of citrus ( $74.28 \pm 3.71\%$ ). Results of potato residue flour are comparable with the values of Bretón-Toral *et al.* (2016) who reported NFE contents in potato peel waste as 51.3%. The high content of NFE in the tested flours reflects their potential for preparation of biodegradable films. These results are similar to the findings of Romelle *et al.* (2016) who reported the chemical composition of different fruit peels (orange peel:  $9.7 \pm 0.6\%$  crude protein,  $14.19 \pm 0.01\%$  crude fiber,  $5.17 \pm 0.98\%$  ash and  $53.27 \pm 0.10\%$  carbohydrates) (apple peel:  $2.80 \pm 0.17\%$  crude protein,  $13.95 \pm 0.10\%$  crude fiber,  $1.39 \pm 0.14\%$  ash and  $59.96 \pm 0.44\%$  carbohydrates).

**Film thickness:** Thickness of the biodegradable film plays a vital role in determining the other physical properties of film including mechanical and water vapor permeability (Laohakunjit and Noomhorm, 2004). At 25% glycerol

**Table 1. Proximate composition of potato, citrus and apple residue flours**

Film material	Moisture (%)	Ash (%)	Protein (%)	Fat (%)	Fiber (%)	NFE (%)
PRF	13.33±0.66	9.38±0.46	15.31±0.76	2.61±0.13	1.40±0.07	57.97±2.89
CRF	10.00±0.50	4.89±0.24	4.37±0.21	4.46±0.22	2.00±0.10	74.28±3.71
ARF	3.30±0.16	2.39±0.11	8.33±0.41	4.59±0.22	2.00±0.10	79.39±3.96

PRF: Potato residue flour; CRF: Citrus residue flour; ARF: Apple residue flour

concentration, minimum thickness was observed in apple residue film followed by citrus residue film and potato residue film. The results showed that glycerol concentration had a highly significant effect on films thickness. The increase in glycerol concentration in film forming solutions caused an increase in the thickness of all the films irrespective of the raw material used (Table 2). Higher film thickness with greater glycerol concentration might be due to the presence of higher dry matter contents in film forming solutions (Nemet *et al.*, 2010). These results are similar to the findings of Kang and Min (2010) who developed potato peel based biodegradable films with 0.1mm thickness. Rezvani *et al.* (2013) reported that the thickness of the films prepared by using different concentrations of sodium caseinate and stearic acid ranged from 0.12 mm to 0.18 mm. The present results are also similar to the findings of Kechichian *et al.* (2010) who formulated cassava starch based biodegradable films incorporated with natural antimicrobial agents.

**Water vapor permeability:** Minimum WVP was observed in apple residue film followed by citrus and potato residue film. Lower WVP values of apple residue films has also been reported in previous study by Vargas *et al.* (2008) who explained that the higher WVP of potato residue films were due to the higher starch contents present in potato peels. Sablani *et al.* (2009) also reported the lower WVP of apple peel based edible films than potato and corn starch based edible films. The results showed that glycerol concentration had a significant effect on WVP of the films. The increase in glycerol concentration in film forming solutions caused an increase in WVP of all the films (Table 2). The increase in WVP might be due to the effect that the inclusion of glycerol molecules between polymer chains increased the molecular

mobility in the film matrix by decreasing intermolecular attractions (increased inter-chain space). Resultantly, this increased mobility produced greater free volume in the matrix which allowed the movement of water vapor molecules through the film (Sothornvit and Krochta, 2000; Rodríguez *et al.*, 2006). The increase in WVP could also be related with the high hydrophilicity of glycerol molecules which is favorable to the adsorption of water molecules (Kang and Min, 2010). A comparison of these results can be made with the conclusions of Sablani *et al.* (2009) who developed apple peels based edible films and reported that highest WVP values were observed at increased glycerol level (44%). Kang and Min (2010) also formulated potato peel based edible films and concluded that the increased glycerol concentration caused an increase in WVP of the films.

**Opacity:** Opacity of the films is the property of prime importance in food packaging and coating. It provides information about the dispersed particles in carbohydrate-based films. Particle sizes larger than visible wavelength cause hinderance in light and produce opaque or translucent films (Kampeerapappun *et al.*, 2007). Lower opacity values (Table 2) represent more transparency. Residue films prepared with 25% glycerol concentration showed greater transparency. Among the prepared films, apple residue film was more transparent followed by citrus and potato residue film. Greater transparency of apple and citrus residue films might be due to the presence of higher pectin contents in these residue films as also reported by Venkatesh and Sutariya (2019). Results showed that glycerol concentration had a highly significant effect on films opacity. The increase in glycerol concentration in film forming solutions caused a decrease in film transparency (Table 2). The results depicted

**Table 2. Effect of glycerol on physical characteristics of the films prepared from potato, citrus and apple residue films**

Film material	Grams in 97ml film forming solution	Glycerol (%) (w/w)	Thickness (mm)	WVP (g mm/kPa h m <sup>2</sup> )	Opacity (AU nm)
PRF	3	25	0.07±0.0044 <sup>ef</sup>	2.81±0.33 <sup>ab</sup>	81.23±1.02 <sup>d</sup>
PRF		30	0.10±0.0078 <sup>c</sup>	3.29±0.38 <sup>ab</sup>	85.10±1.03 <sup>c</sup>
PRF		35	0.17±0.0045 <sup>a</sup>	3.97±0.60 <sup>a</sup>	97.45±1.36 <sup>a</sup>
CRF		25	0.06±0.0054 <sup>fg</sup>	2.75±0.35 <sup>ab</sup>	70.45±1.31 <sup>e</sup>
CRF		30	0.10±0.0065 <sup>cd</sup>	3.15±0.54 <sup>ab</sup>	78.12±1.15 <sup>d</sup>
CRF		35	0.13±0.0072 <sup>b</sup>	3.46±0.56 <sup>ab</sup>	89.45±1.19 <sup>b</sup>
ARF		25	0.05±0.0058 <sup>g</sup>	2.48±0.41 <sup>b</sup>	63.03±1.11 <sup>f</sup>
ARF		30	0.08±0.0053 <sup>de</sup>	3.01±0.49 <sup>ab</sup>	72.11±1.04 <sup>e</sup>
ARF		35	0.10±0.0078 <sup>c</sup>	3.34±0.31 <sup>ab</sup>	85.76±1.01 <sup>c</sup>

PRF: Potato residue films; CRF: Citrus residue films; ARF: Apple residue films

that the thicker films showed greater opacity values compared to the films having lower thickness. Wu *et al.* (2009) explained this phenomenon as thickness of the films influenced the transmittance of light through the film resulting in the more opaque film. Mali *et al.* (2004) also demonstrated that opacity of the yam starch films also increased with the increase in film thickness. Transparency of the films is only required when the packaged food has to be visible. While, mechanical and barrier properties of the films depend upon the concentration of glycerol in film forming solutions. The increase in opacity with higher glycerol concentration might be due to the increased compaction of polymeric chain which modified the refractive index resulting in the restriction of passage of light passing through the film matrix (Saber *et al.*, 2016). Similar results were also reported by Paschoalick *et al.* (2003) and do Amaral Sobral *et al.* (2004). These authors related this phenomenon with the physical characteristics of the plasticizer and its dilution effect in the film forming solution. The results of the present study are in agreement with the findings of Shaw *et al.* (2002) who also found increased films opacity with increased glycerol concentrations.

**Mechanical properties:** Mechanical properties of films are required to sustain their integrity when applied to a food product. Tensile strength is the maximum tension which a film can support (Pereda *et al.*, 2012). Among the prepared films, potato residue film showed greater tensile strength followed by citrus and apple residue film. Greater tensile strength of potato residue film was due to the presence of higher starch contents which formed a more compact and cohesive polymeric matrix (Ferreira *et al.*, 2016). The results depicted that glycerol concentration had a highly significant effect on tensile strength of residue films. The increase in glycerol concentration in film forming solution caused a decrease in tensile strength of the films (Table 3). This decrease in tensile strength of the residue films might be explained by the plasticizing effect of glycerol that formed more homogeneous aggregation of biopolymer materials. This effect might increase the intermolecular spaces between the biopolymer molecules and produced a greater free volume

resulting in the film flexibility (Sablani *et al.*, 2009). Similar results were also observed by Sablani *et al.* (2009) who developed apple peel films and stated that increased glycerol concentration caused a decrease in tensile strength of the films. These findings are also in accordance with the results of Kang and Min (2010) who prepared potato peel films and reported that greater increase in glycerol concentration lessened the tensile strength of the films. Decrease in tensile strength of the films with the increase in glycerol concentration was also reported in previous studies (McHugh and Krochta, 1994; Park *et al.*, 1994; Butler *et al.*, 1996).

Elastic modulus of the film is its ability to resist its deformation against the stress applied. Citrus residue film showed greater elastic modulus followed by potato residue film and apple residue film. The difference in elastic modulus of these films could be attributed to the difference in the ratio of dietary fibers to total sugars (McHugh and Olsen, 2004). The results depicted that glycerol concentration had a highly significant effect on elastic modulus of residue films. The increase in glycerol concentration in film forming solution caused a decrease in elastic modulus of the films (Table 3). The decrease in elastic modulus of residue films with the increased glycerol concentration could be due to the plasticizing effect of glycerol. This effect increased the free volume by increasing intermolecular spaces between the biopolymer chains, which enhanced the film flexibility (Sablani *et al.*, 2009). These results are similar to the findings of Kang and Min (2010) who prepared potato peel based biopolymer films with varying concentrations of glycerol and reported that the elastic modulus of the films decreased with the increasing concentration of glycerol. However, these values are lower than the values reported by Zhang and Whistler (2004) who prepared corn hull arabinoxylan based thin film. Sablani *et al.* (2009) formulated apple peel based edible films and described the similar trend of decreased elastic modulus with increased glycerol concentration.

The maximum variation in length of a film prior to breakage after being subjected to tension is called elongation at break (Pereda *et al.*, 2012). Apple residue film showed higher elongation at break followed by citrus residue film and potato

**Table 3. Effect of glycerol on mechanical properties of the films prepared from potato, citrus and apple residue films**

Film material	Grams in 97ml film forming solution	Glycerol (%) (w/w)	Tensile strength (MPa)	Elastic modulus (MPa)	Elongation at break (%)	Puncture strength (N)
PRF	3	25	8.99±1.23 <sup>a</sup>	352.38±3.67 <sup>d</sup>	9.54±2.59 <sup>b</sup>	13.78±0.65 <sup>a</sup>
PRF		30	7.73±1.22 <sup>a</sup>	237.88±4.58 <sup>e</sup>	10.33±3.61 <sup>b</sup>	12.01±0.21 <sup>b</sup>
PRF		35	5.98±1.07 <sup>ab</sup>	180.91±2.34 <sup>f</sup>	11.49±2.16 <sup>ab</sup>	10.54±0.43 <sup>c</sup>
CRF		25	7.15±1.55 <sup>a</sup>	720.01±2.90 <sup>a</sup>	10.34±3.24 <sup>bc</sup>	10.01±0.54 <sup>cd</sup>
CRF		30	6.87±1.17 <sup>a</sup>	576.23±5.32 <sup>b</sup>	14.99±3.02 <sup>abc</sup>	8.88±0.33 <sup>de</sup>
CRF		35	6.01±1.05 <sup>ab</sup>	441.78±5.43 <sup>c</sup>	19.81±2.86 <sup>a</sup>	6.55±0.21 <sup>g</sup>
ARF		25	3.19±1.03 <sup>bc</sup>	40.85±6.79 <sup>g</sup>	11.87±3.55 <sup>abc</sup>	8.15±0.67 <sup>ef</sup>
ARF		30	2.89±1.01 <sup>bc</sup>	36.78±6.09 <sup>g</sup>	13.31±3.61 <sup>abc</sup>	7.12±0.25 <sup>fg</sup>
ARF		35	1.99±0.12 <sup>c</sup>	33.67±4.54 <sup>g</sup>	16.03±2.34 <sup>ab</sup>	4.98±0.15 <sup>h</sup>

PRF: Potato residue films; CRF: Citrus residue films; ARF: Apple residue films

residue film. The results depicted that glycerol concentration had a significant effect on elongation at break of residue films. The increase in glycerol concentration in film forming solution caused an increase in elongation at break of residue films (Table 3). The increase in elongation at break percentage might be due to the effect that glycerol is more hygroscopic in nature due to its lower molecular weight and thus, increased glycerol concentration caused an increase in film plasticization (Zhang and Whistler, 2004). Kang and Min (2010) prepared potato peel based biopolymer films and found a decrease in elastic modulus and increase in elongation at break of biopolymer film with increased glycerol concentration. Sablani *et al.* (2009) also demonstrated the similar results that with increased glycerol concentration, elastic modulus decreased and elongation at break of apple peel based edible film was found to increase. The percent elongation of these residue films were also comparable with the results of Fai *et al.* (2016) who prepared biodegradable films from fruits and vegetable residues and reported that the percent elongation of films were in the range of 13 to 17%. Potato residue film showed more puncture strength than citrus and apple residue film. The greater puncture strength of potato residue film might be due to the presence of higher starch contents in potato residue. The results depicted that glycerol concentration had a highly significant effect on puncture strength of the prepared films. The increase in glycerol concentration in film forming solution caused a decrease in puncture strength of the films (Table 3). Puncture strength of the films depends upon the film thickness as well as the concentration of glycerol in the film forming solutions. The puncture strength of the films increases with increasing film thickness. This effect of film thickness on puncture strength was observed by Sobral (2000) in protein films. The author utilized a higher mass of same film forming solution and developed thicker films. The decrease in puncture strength with increased glycerol concentration was also reported by Mali *et al.* (2004) who postulated that puncture strength of yam starch films was influenced by the glycerol concentration in the film forming solution, film thickness and concentration of the starch. The authors further suggested that higher starch concentration, higher film thickness with lower glycerol contents produced films with higher puncture strength. These results also confirmed the observations of Mali and Grossmann (2003) who reported that the intermolecular forces along polymer chains decreased with increased plasticizer resulting in the increased film flexibility and decreased barrier properties.

**Photo oxidation:** Fourier Transform Infrared Spectroscopy (FTIR) technique was used to measure the structure of organic compounds present in prepared biodegradable films. FTIR analysis also exhibited the bonding between glycerol and the carbohydrate contents present in the raw material used. FTIR spectra of the films prepared from potato, citrus and apple residues have been presented in Fig. 1, 2 and 3, respectively.




Figure 1. FTIR spectra of potato residue film (a: 25%, b: 30% and c: 35% glycerol)




Figure 2. FTIR spectra of citrus residue film (a: 25%, b: 30% and c: 35% glycerol)




Figure 3. FTIR spectra of apple residue film (a: 25%, b: 30% and c: 35% glycerol)

FTIR spectra of potato residue films (Fig. 1) depicted that hydroxyl stretching vibration caused the formation of a broad band in the region of  $3361\text{cm}^{-1}$  and the band in the region of  $2931\text{cm}^{-1}$  was because of the presence of  $\text{CH}_2$  symmetric and

asymmetric stretching vibration (Demirgoz *et al.*, 2000; Xu *et al.*, 2004). CH<sub>2</sub> bending vibration formed a peak at 1435 cm<sup>-1</sup> (Kim *et al.*, 2003). The higher moisture content in the film caused the appearance of water absorption wavelength at 1642 cm<sup>-1</sup>. The spectra of the films prepared with lower glycerol concentrations in the film forming solutions showed decreased and narrower peaks indicating the hydrogen interaction between glycerol and starch. Additionally, it was also due to the lower plasticization effect as reported by Liu *et al.* (2014). The FTIR spectra of the current study are almost similar to the spectra obtained by Guohua *et al.* (2006) and Sharif *et al.* (2019). FTIR spectra of citrus residue films depicted the most intense band in the region of 3412cm<sup>-1</sup> due to the presence of OH in carbohydrate contents of the citrus residue (Fig. 2). C-H stretching vibration and bending vibrations formed a distinctive band at 2978 cm<sup>-1</sup> and 1437 cm<sup>-1</sup>, respectively. The appearance of the peak at 1698 cm<sup>-1</sup> might be due to the aliphatic and/or unsaturated aromatic compounds as also reported by Demirbas (2000) and McKendry (2002). Similar findings were also observed by Zapata *et al.* (2009) while conducting the thermo kinetics study of orange peel in air. Furthermore, the spectra of the current study also resemble with the spectra observed by Arslanoglu *et al.* (2008). The FTIR spectra of apple residue films also showed the peak close to the citrus residue films (Fig. 3). However, the absorbance was lower than that of citrus residue films. The absorbance peaks were observed in the region of 3382 cm<sup>-1</sup> and 2983 cm<sup>-1</sup>. This might be due to the presence of OH bonding in the pectin structure of the apple residue and C-H stretching, respectively. The absorbance peak at 1673 cm<sup>-1</sup> might be due to the presence of high methoxly pectin (Gnanasambandam and Proctor, 2000). Similar spectra were also recorded by Urias-Orona *et al.* (2010). The spectra of the citrus and apple residue films prepared with lower glycerol concentrations in the film forming solutions showed decreased and narrower peaks indicating the hydrogen interaction between glycerol and pectin.

**Conclusions:** Among the three biodegradable films prepared from potato, citrus and apple residues, potato residue film exhibited optimum thickness, good resistance to water vapor transmission and mechanical properties compared to citrus and apple residue films. Opacity of potato residue films was slightly higher than other films. The varying concentration of glycerol significantly affected the properties of the prepared films. Increased glycerol concentration in film forming solutions resulted in an increase in thickness, opacity, elongation at break and water vapor permeability of all the films. However, increased glycerol concentration caused a decrease in tensile strength, elastic modulus and puncture strength of all the films.

## REFERENCES

- Aacc. 2000. Approved methods of the American Association of Cereal Chemists. 11<sup>th</sup> edition. AACC Press, MN, USA.
- Aguilar-Mendez, M.A., E.S. Martin-Martinez, S.A. Tomas, A. Cruz-Orea and M.R. Jaime-Fonseca. 2008. Gelatine–starch films: Physicochemical properties and their application in extending the post-harvest shelf life of avocado (*Persea americana*). *J. Sci. Food Agric.* 88:185-193.
- Ahmed, J., Hafeezullah and S. Amin 2017. Fruit, vegetables and condiments statistics of Pakistan 2015-16.
- Ajila, C. and U.P. Rao. 2013. Mango peel dietary fibre: Composition and associated bound phenolics. *J. Funct. Foods.* 5:444-450.
- Akpabio, U.D., A.E. Akpakpan and G.N. Enin. 2012. Evaluation of proximate compositions and mineral elements in the star apple peel, pulp and seed. *Magnesium (Mg).* 6:29-49.
- Ali, S.W., A. Nawaz, S. Irshad and A.A. Khan. 2015. Potato waste management in Pakistan's perspective. *J. Hyg. Eng. Des.* 13:100-107.
- Almasi, H., B. Ghanbarzadeh and A.A. Entezami. 2010. Physicochemical properties of starch–CMC–nanoclay biodegradable films. *Int. J. Biol. Macromol.* 46:1-5.
- Almenar, E., H. Samsudin, R. Auras and J. Harte. 2010. Consumer acceptance of fresh blueberries in bio-based packages. *J. Sci. Food Agric.* 90:1121-1128.
- Alves, V.D., N. Costa and I.M. Coelho. 2010. Barrier properties of biodegradable composite films based on kappa-carrageenan/pectin blends and mica flakes. *Carbohydr. Polym.* 79:269-276.
- Arslanoglu, H., H.S. Altundogan and F. Tumen. 2008. Preparation of cation exchanger from lemon and sorption of divalent heavy metals. *Bioresour. Technol.* 99:2699-2705.
- Athmaselvi, K., P. Sumitha and B. Revathy. 2013. Development of *Aloe vera* based edible coating for tomato. *Int. Agrophys.* 27:369-375.
- Azeredo, H.M., L.H.C. Mattoso, D. Wood, T.G. Williams, R.J. Avena-Bustillos and T.H. Mchugh. 2009. Nanocomposite edible films from mango puree reinforced with cellulose nanofibers. *J. Food Sci.* 74:31-35.
- Azeredo, H.M., K.W. Miranda, M.F. Rosa, D.M. Nascimento and M.R. De Moura. 2012. Edible films from alginate-acerola puree reinforced with cellulose whiskers. *LWT-Food Sci. Technol.* 46:294-297.
- Babbar, N., H.S. Oberoi, D.S. Uppal and R.T. Patil. 2011. Total phenolic content and antioxidant capacity of extracts obtained from six important fruit residues. *Food Res. Int.* 44:391-396.

- Banisadr, S. and H. Asempour. 2012. Effect of ferric salt of orange peel solid fraction on photo-oxidation and biodegradability of LDPE films. *Iran. Polym. J.* 21:463-471.
- Benítez, S., I. Achaerandio, F. Sepulcre and M. Pujolà. 2013. *Aloe vera* based edible coatings improve the quality of minimally processed 'Hayward' kiwifruit. *Postharvest Biol. Technol.* 81:29-36.
- Bretón-Toral, A., S. Trejo-Estrada and A. McDonald. 2016. Lactic acid production from potato peel waste, spent coffee grounds and almond shells with undefined mixed cultures isolated from coffee mucilage from Coatepec Mexico. *Ferment. Technol.* 6:1-6.
- Butler, B., P. Vergano, R. Testin, J. Bunn and J. Wiles. 1996. Mechanical and barrier properties of edible chitosan films as affected by composition and storage. *J. Food Sci.* 61:953-956.
- Campos, D., C. Piccirillo, R.C. Pullar, P.M. Castro and M.M. Pintado. 2014. Characterization and antimicrobial properties of food packaging methylcellulose films containing stem extract of Ginja cherry. *J. Sci. Food Agric.* 94:2097-2103.
- Cardoso, T., I.M. Demiate and E.D.G. Danesi. 2017. Research Article Biodegradable Films with *Spirulina platensis* as Coating for Cambuci Peppers (*Capsicum sp.*). *Am. J. Food Technol.* 12:236-244.
- Cerqueira, M., A. Bourbon, A. Pinheiro, J. Martins, B. Souza, J. Teixeira and A. Vicente. 2011. Galactomannans use in the development of edible films/coatings for food applications. *Trends Food Sci. Technol.* 22:662-671.
- Chauhan, S., K. Gupta and M. Agrawal. 2014. Application of biodegradable *Aloe vera* gel to control post-harvest decay and longer the shelf life of Grapes. *Int. J. Curr. Microbiol. Appl. Sci.* 3:632-642.
- Chiumarelli, M. and M.D. Hubinger. 2012. Stability, solubility, mechanical and barrier properties of cassava starch-Carnauba wax edible coatings to preserve fresh-cut apples. *Food Hydrocolloids.* 28:59-67.
- Chonhenchob, V., Y. Chantarasomboon and S.P. Singh. 2007. Quality changes of treated fresh-cut tropical fruits in rigid modified atmosphere packaging containers. *Packag. Technol. Sci.: An Int. J.* 20:27-37.
- Cortez-Vega, W.R., S. Pizato, J.T.A. De Souza and C. Prentice. 2014. Using edible coatings from Whitemouth croaker (*Micropogonias furnieri*) protein isolate and organo-clay nanocomposite for improve the conservation properties of fresh-cut 'Formosa' papaya. *Innov. Food Sci. Emerg. Technol.* 22:197-202.
- Del Nobile, M., A. Conte, M. Cannarsi and M. Sinigaglia. 2008. Use of biodegradable films for prolonging the shelf life of minimally processed lettuce. *J. Food Eng.* 85:317-325.
- Demirbas, A. 2000. Mechanisms of liquefaction and pyrolysis reactions of biomass. *Energy Convers. Manag.* 41:633-646.
- Demirgoz, D., C. Elvira, J.F. Mano, A.M. Cunha, E. Piskin and R.L. Reis. 2000. Chemical modification of starch based biodegradable polymeric blends: Effects on water uptake, degradation behaviour and mechanical properties. *Polym. Degrad. Stab.* 70:161-170.
- Do Amaral Sobral, P.J., F.T. Garcia, A.M.Q.B. Habitante and E.S. Monterrey-Quintero. 2004. Properties of edible films produced with different concentrations of plasticizers and Nile tilapia muscle proteins. *Brazil. Agric. Res.* 39:255-262.
- Du, W.X., C. Olsen, R. Avena-Bustillos, M. Friedman and T. Mchugh. 2011. Physical and antibacterial properties of edible films formulated with apple skin polyphenols. *J. Food Sci.* 76:149-155.
- Du, W.X., C. Olsen, R. Avena-Bustillos, T. Mchugh, C. Levin and M. Friedman. 2008. Antibacterial activity against *E. coli* O157: H7, physical properties, and storage stability of novel carvacrol-containing edible tomato films. *J. Food Sci.* 73:378-383.
- Expresswire, T. 2019. Global Packaging Materials Market 2019 Supply, Consumption, Cost and Profit analysis and forecast to 2025. . <https://www.marketwatch.com/press-release/global-packaging-materials-market-2019-supply-consumption-cost-and-profit-analysis-and-forecast-to-2025-2019-11-20> accessed on 27-01-2020. Market Watch.
- Fai, A.E.C., M.R.A. De Souza, S.T. De Barros, N.V. Bruno, M.S.L. Ferreira and E.C.B. De Andrade Gonçalves. 2016. Development and evaluation of biodegradable films and coatings obtained from fruit and vegetable residues applied to fresh-cut carrot (*Daucus carota* L.). *Postharvest Biol. Technol.* 112:194-204.
- Fakhouri, F.M., S.M. Martelli, T. Caon, J.I. Velasco and L.H.I. Mei. 2015. Edible films and coatings based on starch/gelatin: Film properties and effect of coatings on quality of refrigerated Red Crimson grapes. *Postharvest Biol. Technol.* 109:57-64.
- Ferreira, M.S., A.E.C. Fai, C.T. Andrade, P.H. Picciani, E.G. Azero and É.C. Gonçalves. 2016. Edible films and coatings based on biodegradable residues applied to acerolas (*Malpighia puniceifolia* L.). *J. Sci. Food Agric.* 96:1634-1642.
- Ferreira, M.S., M.C. Santos, T.M. Moro, G.J. Basto, R.M. Andrade and É.C. Gonçalves. 2015. Formulation and characterization of functional foods based on fruit and vegetable residue flour. *J. Sci. Food Agric.* 52:822-830.
- Franco, M.J., A.A. Martin, L.F. Bonfim Jr, J. Caetano, G.A. Linde and D.C. Dragunski. 2017. Effect of plasticizer and modified starch on biodegradable films for strawberry protection. *J. Food Process. Preserv.* 41:1-9.

- Gnanasambandam, R. and A. Proctor. 2000. Determination of pectin degree of esterification by diffuse reflectance Fourier transform infrared spectroscopy. *Food Chem.* 68:327-332.
- Gol, N.B., M.L. Chaudhari and T.R. Rao. 2015. Effect of edible coatings on quality and shelf life of carambola (*Averrhoa carambola* L.) fruit during storage. *J. Food Sci. Technol.* 52:78-91.
- Gol, N.B., P.R. Patel and T.R. Rao. 2013. Improvement of quality and shelf-life of strawberries with edible coatings enriched with chitosan. *Postharvest Biol. Technol.* 85:185-195.
- Guohua, Z., L. Ya, F. Cuilan, Z. Min, Z. Caiqiong and C. Zongdao. 2006. Water resistance, mechanical properties and biodegradability of methylated-cornstarch/poly (vinyl alcohol) blend film. *Polym. Degrad. Stab.* 91:703-711.
- Kadzińska, J., M. Janowicz, S. Kalisz, J. Bryś and A. Lenart. 2019. An overview of fruit and vegetable edible packaging materials. *Packag. Technol. Sci.* 32:483-495.
- Kampeerappun, P., D. Aht-Ong, D. Pentrakoon and K. Srikulkit. 2007. Preparation of cassava starch/montmorillonite composite film. *Carbohydr. Polym.* 67:155-163.
- Kang, H.J. and S.C. Min. 2010. Potato peel-based biopolymer film development using high-pressure homogenization, irradiation, and ultrasound. *LWT-Food Science and Technology.* 43:903-909.
- Kechichian, V., C. Ditchfield, P. Veiga-Santos and C.C. Tadini. 2010. Natural antimicrobial ingredients incorporated in biodegradable films based on cassava starch. *LWT-Food Science and Technology.* 43:1088-1094.
- Khalil, H.A., A. Banerjee, C.K. Saurabh, Y. Tye, A. Suriani, A. Mohamed, A. Karim, S. Rizal and M. Paridah. 2018. Biodegradable films for fruits and vegetables packaging application: Preparation and properties. *Food Eng. Rev.* 10:139-153.
- Kim, D.H., S.K. Na and J.S. Park. 2003. Preparation and characterization of modified starch-based plastic film reinforced with short pulp fiber. I. Structural properties. *J. Appl. Polym. Sci.* 88:2100-2107.
- Laohakunjit, N. and A. Noomhorm. 2004. Effect of plasticizers on mechanical and barrier properties of rice starch film. *Starch-Starke.* 56:348-356.
- Liu, K., C. Yuan, Y. Chen, H. Li and J. Liu. 2014. Combined effects of ascorbic acid and chitosan on the quality maintenance and shelf life of plums. *Sci. Hort.* 176:45-53.
- Lorevice, M.V., M.R.D. Moura, F.A. Aouada and L.H. Mattoso. 2012. Development of novel guava puree films containing chitosan nanoparticles. *J. Nanosci. Nanotechnol.* 12:2711-2717.
- Mali, S. and M.V.E. Grossmann. 2003. Effects of yam starch films on storability and quality of fresh strawberries (*Fragaria ananassa*). *J. Agric. Food Chem.* 51:7005-7011.
- Mali, S., M.V.E. Grossmann, M.A. Garcia, M.N. Martino and N.E. Zaritzky. 2004. Barrier, mechanical and optical properties of plasticized yam starch films. *Carbohydr. Polym.* 56:129-135.
- Manneppula, S., V.K. Bathal and V.S.R. Obulam. 2015. A comparative study on utilisation of citrus and mango peels for lactic acid production and optimisation by *Rhizopus oryzae* in submerged fermentation. *Eur. J. Biotechnol. Biosci.* 3:18-26.
- Martelli, M.R., T.T. Barros, M.R. De Moura, L.H. Mattoso and O.B. Assis. 2013. Effect of chitosan nanoparticles and pectin content on mechanical properties and water vapor permeability of banana puree films. *J. Food Sci.* 78:98-104.
- Mchugh, T. and C. Olsen. 2004. Tensile properties of fruit and vegetable edible films. *United States-Japan Cooperative Program in Natural Resources.* 104-108.
- Mchugh, T. and E. Senesi. 2000. Apple wraps: A novel method to improve the quality and extend the shelf life of fresh-cut apples. *J. Food Sci.* 65:480-485.
- Mchugh, T.H. and J.M. Krochta. 1994. Sorbitol-vs glycerol-plasticized whey protein edible films: Integrated oxygen permeability and tensile property evaluation. *J. Agric. Food Chem.* 42:841-845.
- Mckendry, P. 2002. Energy production from biomass (part 1): Overview of biomass. *Bioresour. Technol.* 83:37-46.
- Mensitieri, G., E. Di Maio, G.G. Buonocore, I. Nedi, M. Oliviero, L. Sansone and S. Iannace. 2011. Processing and shelf life issues of selected food packaging materials and structures from renewable resources. *Trends Food Sci. Technol.* 22:72-80.
- Moreira, M.D.R., M. Pereda, N.E. Marcovich and S.I. Roura. 2011. Antimicrobial effectiveness of bioactive packaging materials from edible chitosan and casein polymers: Assessment on carrot, cheese, and salami. *J. Food Sci.* 76:54-63.
- Nemet, N., V. Soso and V. Lazic. 2010. Effect of glycerol content and pH value of film-forming solution on the functional properties of protein-based edible films. *Acta Period. Technol.* 41:47-57.
- Orsuwan, A., S. Shankar, L.-F. Wang, R. Sothornvit and J.-W. Rhim. 2016. Preparation of antimicrobial agar/banana powder blend films reinforced with silver nanoparticles. *Food Hydrocolloids.* 60:476-485.
- Park, H.J., J. Bunn, C.L. Weller, P. Vergano and R. Testin. 1994. Water vapor permeability and mechanical properties of grain protein-based films as affected by mixtures of polyethylene glycol and glycerin plasticizers. *Trans. ASAE.* 37:1281-1285.

- Park, S.I. and Y. Zhao. 2006. Development and characterization of edible films from cranberry pomace extracts. *Journal of Food Science*. 71:95-101.
- Paschoalick, T., F. Garcia, P.D.A. Sobral and A. Habitante. 2003. Characterization of some functional properties of edible films based on muscle proteins of Nile Tilapia. *Food Hydrocolloids*. 17:419-427.
- Pereda, M., G. Amica and N.E. Marcovich. 2012. Development and characterization of edible chitosan/olive oil emulsion films. *Carbohydr. Polym.* 87:1318-1325.
- Pitak, N. and S.K. Rakshit. 2011. Physical and antimicrobial properties of banana flour/chitosan biodegradable and self sealing films used for preserving fresh-cut vegetables. *LWT-Food Sci. Technol.* 44:2310-2315.
- Ravishankar, S., D. Jaroni, L. Zhu, C. Olsen, T. Mchugh and M. Friedman. 2012. Inactivation of *Listeria monocytogenes* on ham and bologna using pectin-based apple, carrot, and hibiscus edible films containing carvacrol and cinnamaldehyde. *J. Food Sci.* 77:377-382.
- Rezvani, E., G. Schleining, G. Sümen and A.R. Taherian. 2013. Assessment of physical and mechanical properties of sodium caseinate and stearic acid based film-forming emulsions and edible films. *J. Food Eng.* 116:598-605.
- Rodríguez, M., J. Oses, K. Ziani and J.I. Mate. 2006. Combined effect of plasticizers and surfactants on the physical properties of starch based edible films. *Food Res. Int.* 39:840-846.
- Romelle, F.D., R. Ashwini and R.S. Manohar. 2016. Chemical composition of some selected fruit peels. *Eur. J. Food Sci. Technol.* 4:12-21.
- Saberi, B., R. Thakur, Q.V. Vuong, S. Chockchaisawasdee, J.B. Golding, C.J. Scarlett and C.E. Stathopoulos. 2016. Optimization of physical and optical properties of biodegradable edible films based on pea starch and guar gum. *Ind. Crop. Prod.* 86:342-352.
- Sablani, S.S., F. Dasse, L. Bastarrachea, S. Dhawan, K.M. Hendrix and S.C. Min. 2009. Apple Peel-Based Edible Film Development Using a High-Pressure Homogenization. *J. Food Sci* 74:372-381.
- Sangsuwan, J., N. Rattanapanone and P. Rachtanapun. 2008. Effect of chitosan/methyl cellulose films on microbial and quality characteristics of fresh-cut cantaloupe and pineapple. *Postharvest Biol. Technol.* 49:403-410.
- Saravacos, G., P. Taoukis, M. Krokida, V. Karathanos, H. Lazarides, N. Stoforos, C. Tzia, S. Yanniotis, V.D. Alves, R. Castello, A.R. Ferreira, N. Costa, I.M. Fonseca and I.M. Coelho. 2011. 11th International Congress on Engineering and Food (ICEF11). Barrier properties of carrageenan/pectin biodegradable composite films. *Procedia Food Sci.* 1:240-245.
- Shahbandeh, M. 2019. Global market value of food packaging from 2018-2025 .<https://www.statista.com/statistics/876489/food-packaging-market-value-forecast-worldwide/>. Accessed on 27 January 2020. *Statista* 2020.
- Sharif, Z., J. Jai, I. Subuki, N. Zaki, F. Mustapha, N.M. Yusof and S. Idris. Optimization of Starch Composite Edible Coating Formulation on Fresh-Cut “Fuji” Apple through Surface Tension, Wettability and FTIR Spectroscopy. *IOP Conference Series: Materials Science and Engineering*, 2019. IOP Publishing, 1-6.
- Shaw, N., F. Monahan, E. O’riordan and M. O’sullivan. 2002. Effect of soya oil and glycerol on physical properties of composite WPI films. *J. Food Eng.* 51:299-304.
- Shen, Z., M. Ghasemlou and D.P. Kamdem. 2015. Development and compatibility assessment of new composite film based on sugar beet pulp and polyvinyl alcohol intended for packaging applications. *J. Appl. Polym. Sci.* 132:1-8.
- Siracusa, V., P. Rocculi, S. Romani and M. Dalla Rosa. 2008. Biodegradable polymers for food packaging: A review. *Trends Food Sci. Technol.* 19:634-643.
- Sobral, P.D.A. 2000. Influence of the biofilm thickness made from myofibrillary proteins on its functional properties. *Brazil. Agric. Res.* 35:1251-1259.
- Sorrentino, A., G. Gorrasi and V. Vittoria. 2007. Potential perspectives of bio-nanocomposites for food packaging applications. *Trends Food Sci. Technol.* 18:84-95.
- Sothornvit, R. and J. Krochta. 2000. Plasticizer effect on oxygen permeability of  $\beta$ -lactoglobulin films. *J. Agric. Food Chem.* 48:6298-6302.
- Sothornvit, R. and N. Pitak. 2007. Oxygen permeability and mechanical properties of banana films. *Food Res. Int.* 40:365-370.
- Tapia, M., M. Rojas-Graü, A. Carmona, F. Rodríguez, R. Soliva-Fortuny and O. Martin-Belloso. 2008. Use of alginate-and gellan-based coatings for improving barrier, texture and nutritional properties of fresh-cut papaya. *Food Hydrocolloids*. 22:1493-1503.
- Torres, C.A., L.A. Romero and R.I. Diaz. 2015. Quality and sensory attributes of apple and quince leathers made without preservatives and with enhanced antioxidant activity. *LWT-Food Sci. Technol.* 62:996-1003.
- Urias-Orona, V., A. Rascón-Chu, J. Lizardi-Mendoza, E. Carvajal-Millán, A.A. Gardea and B. Ramírez-Wong. 2010. A novel pectin material: Extraction, characterization and gelling properties. *Int. J. Mol. Sci.* 11:3686-3695.
- Vargas, M., C. Pastor, A. Chiralt, D.J. McClements and C. Gonzalez-Martinez. 2008. Recent advances in edible coatings for fresh and minimally processed fruits. *Crit. Rev. Food Sci. Nutr.* 48:496-511.
- Venkatesh, A. and H. Sutariya. 2019. Studies on formulation and properties of fruit peel waste incorporated edible film and its effect on quality of bread. *J. Packag. Technol. Res.* 3:99-108.

- Wang, S.Y. and H. Gao. 2013. Effect of chitosan-based edible coating on antioxidants, antioxidant enzyme system, and postharvest fruit quality of strawberries (*Fragaria x ananassa Duch.*). *LWT-Food Sci. Technol.* 52:71-79.
- Wu, H., C. Liu, J. Chen, P.R. Chang, Y. Chen and D.P. Anderson. 2009. Structure and properties of starch/ $\alpha$ -zirconium phosphate nanocomposite films. *Carbohydr. Polym.* 77:358-364.
- Xu, Y., V. Miladinov and M.A. Hanna. 2004. Synthesis and characterization of starch acetates with high substitution. *Cereal Chem.* 81:735-740.
- Zapata, B., J. Balmaseda, E. Fregoso-Israel and E. Torres-Garcia. 2009. Thermo-kinetics study of orange peel in air. *J. Therm. Anal. Calorim.* 98:309-315.
- Zhang, P. and R.L. Whistler. 2004. Mechanical properties and water vapor permeability of thin film from corn hull arabinoxylan. *J. Appl. Polym. Sci.* 93:2896-2902.